

Amendments to the Claims

This listing of claims will replace all prior versions of claims in the application.

1-9. (cancel)

Please insert new claims 10-20 as follows:

10. (New) A heat-curable adhesive composition comprising:
an ethylene-glycidyl (meth)acrylate copolymer;
a low density polyethylene;
an ethylene- α -olefin copolymer; and
a heat curing agent for said ethylene-glycidyl (meth)acrylate copolymer.
11. (New) The heat-curable adhesive composition of claim 10, wherein the minimum density of said low density polyethylene is at least about 0.910 as measured according to ASTM D1248-84.
12. (New) The heat-curable adhesive composition of claim 10, wherein the maximum density of said low density polyethylene is up to about 0.925 as measured according to ASTM D1248-84.
13. (New) The heat-curable adhesive composition of claim 10, wherein, in said ethylene- α -olefin copolymer, the polymerization ratio of ethylene to α -olefin is from about 90:10 to about 10:90.
14. (New) The heat curable adhesive composition of claim 10, wherein the minimum density of said ethylene- α -olefin copolymer is about 0.850 as measured according to ASTM D1248-84.
15. (New) The heat curable adhesive composition of claim 10, wherein the maximum density of said ethylene- α -olefin copolymer is up to about 0.909 as measured according to ASTM D1248-84.

16. (New) The heat-curable adhesive composition of claim 10, wherein said heat curing agent comprises a rosin having a carboxyl group in the molecule.
17. (New) The heat-curable adhesive composition of claim 10, wherein said composition is in the form of a thin film.
18. (New) The heat-curable adhesive composition of claim 17, wherein said film has a thickness from about 5 to about 80 μm .
19. (New) The heat-curable adhesive composition of claim 10, wherein, after post-curing, the composition has a dielectric constant of about 2.5 or less, and a dielectric loss tangent of about 0.015 or less when measured at the frequency of about 1 GHz.
20. (New) The heat-curable adhesive composition of claim 10 having an adhesive.